



MULTICRETE[®] CM

Single Component Cement Mixes Modifier
Product Code No.:M-0303

PRODUCT DESCRIPTION:

MULTICRETE[®] CM is an advanced co-polymer dispersion which, when used as an admixture for cement and/or sand/aggregates mixes, produces a high strength waterproofing coating, patching mortar, screed or render. It can also be mixed with cement to produce a slurry for sealing porous and absorbent substrates. Once applied the mortar has excellent resistance to wash out and cures rapidly to form dense impermeable matrix with high diffusing resistance to oxygen, acid gases and chloride ion.

MULTICRETE[®] CM can also be used to produce Guniting with enhanced properties for application by wet or dry process allowing high build application with low rebound losses at too water- cement ratios.

The enhanced properties ensure high adhesion, low shrinkage, and excellent resistance to freeze - thaw attack and high flexural and compressive strengths.

USES:

MULTICRETE[®] CM is a unique polymer ideally suited for modification of sand and cement mortars, producing hard and spray applied mortars and renders with enhanced polymeric and pozzolanic properties. The Mortars prepared from **MULTICRETE[®] CM** can also be used for pointing of stones, where waterproofing is required. When mixed with cement, the products can also be used as a primer for steel reinforcement and a bonding agent for polymer mortar, renders, concrete and screeds.

ADVANTAGES:

MULTICRETE[®] CM enhances cementitious mixes to give the following properties:

- ❖ Excellent adhesion in dry, damp or permanently wet conditions to both concrete and steel.
- ❖ Higher compressive and tensile strength.
- ❖ High abrasion resistance.
- ❖ Low water permeability due to continued pozzolanic reactions hence has dense matrix.
- ❖ Enhanced resistance to freeze - thaw cycles, alkalis and dilute acids.
- ❖ Low shrinkage.
- ❖ Non Corrosive to steel with high inherent alkalinity,
- ❖ Allows easy application to achieve high application thickness in both vertical and horizontal situations. Resulting spray applied mortar have low rebound losses.



MULTICHEM GROUP | 1, 1st Floor, Kirtida Bungalow, Nahur Stn Road, Beside SBI Bank,
Bhandup (E), Mumbai-400042, Phone No.: 91-22-25669137, 25664890,
e-mail: info@multichemgroup.net, www.multicretecm.com, www.multichemgroup.net

Multicrete CM/1997/R2-13/5/2018



MULTICRETE[®] CM

Single Component Cement Mixes Modifier
Product Code No.:M-0303

TECHNICAL DATA:

Description	Results
Product	Modified Special Resin in Water
Typical Drying Time	2 hours depending on Temperature and substrate
Elongation	500% (without cement)
Coverage	50-60 m ² /Kg
Packaging	200 gm, ½ Kg, 1Kg, 10 Kg, 20 Kg
Storage	Store above 5 °C and below 30 °C
Shelf Life	12 months in above conditions

The following are suggested trial mix ratios by weight based on saturated, surface dry sand and aggregates complying with BS 882: 1994. Trial mixes should be carried out to determine optimum consistency and physical properties for a particular application.

RECOMMENDED MIX DESIGN:

1. FLOOR SCREEDS / TOPPING

CLASS	THICKNESS (mm)	AGGREGATE CEMENT RATIO	DRY SAND (Kg)	DRY AGGREGATE		POLYMER ADMIXTURE MULTICRETE CM	EXTRA* WATER (ltr.)
				SIZE (mm)	WEIGHT (kg)		
LIGHT DUTY	8-15	1:4	200	----	-----	12 litres	4
MEDIUM/ HEAVY DUTY	10-15	1:4	100	3	100	12 litres	8
MEDIUM/ HEAVY DUTY	15-30	1:4	112.5	6	87.5	10 litres	8.5
MEDIUM/ HEAVY DUTY	25-40	1:5	125	10	100	11 litres	7.3

* Adjust water as per need of workability.

NOTES

Mix proportions are based on 50kg of cement.

It is assumed that damp aggregates are used with 5% water in the sand and 1% water in the single sized aggregates. Maximum water additions assume damp aggregates are used and give a maximum water: cement ratio of W: C (0:40).



MULTICHEM GROUP | 1, 1st Floor, Kirtida Bungalow, Nahur Stn Road, Beside SBI Bank, Bhandup (E), Mumbai-400042, Phone No.: 91-22-25669137, 25664890, e-mail: info@multichemgroup.net, www.multicretecm.com, www.multichemgroup.net

Multicrete CM/1997/R2-13/5/2018



MULTICRETE[®] CM

Single Component Cement Mixes Modifier
Product Code No.:M-0303

2. REPAIR MORTAR

Recommended mixes:

Description	Rendering Mortar	Patching Mortar	Heavy Duty Mortar
Portland Cement	50kg.	50 kg.	50 kg.
Medium Grade Sand	150 kg.	150 kg.	75 kg
Granite Aggregate 6mm	-	-	75 kg.
Multicrete CM, Kg	8	10	8
Water*	15 ltr.	15 ltr.	11.5 ltr.
Typical Yield	105 ltr.	105ltr.	95 ltr.
Compressive Strength (28 days Typical)	40N/mmsq.	50N/mmsq	69N/mmsq

* Add water as per required workability.

NOTES

Always use sharp sand. All sand and aggregate must be cleaned and washed. Add the minimum amount of water to give the desired workability, to enable correct working and compaction.

Maximum dilution 1:4 (MULTICRETE[®] CM: water)

3. INTERGRAL WATERPROOFING COMPOUND

Recommended mixes:

Description	Waterproofing of Plaster	Waterproofing of Terrace Slab	Waterproofing of Concrete
Portland Cement	50kg.	50 kg.	50 kg.
Medium Grade Sand	As per clients	As per mix design	As per mix design
Aggregate	-	As per mix design	As per mix design
Multicrete CM, Kg	100-500 gm	200 gm-4 Kg	200 gm-4 Kg
Water	As per need	As per need	As per need
Typical Yield	-	-	-



MULTICHEM GROUP | 1, 1st Floor, Kirtida Bungalow, Nahur Stn Road, Beside SBI Bank, Bhandup (E), Mumbai-400042, Phone No.: 91-22-25669137, 25664890, e-mail: info@multichemgroup.net, www.multicretecm.com, www.multichemgroup.net

Multicrete CM/1997/R2-13/5/2018



MULTICRETE[®] CM

Single Component Cement Mixes Modifier
Product Code No.:M-0303

4. WATERPROOFING COATINGS

Recommended mixes:

Description	Flexible Coating	Hard Coating	Crack Repair Mortar
Portland Cement	50kg.	50 kg.	50 kg.
Fine Sand Powder(<0.3mm)	0.0	100 kg.	75 kg.
Quartz Sand(< 1mm)	0.0	0.0	75 kg.
Multicrete CM	50-100 kg	50	10 kg
Water	0.0.	0.0	As required
Typical Coverage	10 to 15 ft2 per kg of Multicrete CM used	10 to 15 ft2 per kg of Multicrete CM used	As per crack width

Note: Following are mix ratio designs for waterproofing coatings.

Minimum Ratio: Minimum=cm: cement: 1 : 1 to 2 kg, Coverage: 20 ft2 for two coats

Medium Ratio= CM: water: cement= 1: 2.5 : 4 kg, Coverage: 35 ft2 for two coats

Maximum Ration= CM: Water: Cement= 1 : 4 : 7 kg, Coverage: 70 to 80 ft2 for two coats

5. TILE ADHESIVE

Recommended mixes:

Description	Adhesive for Tile on Tile	Standard Adhesive	Heavy Duty Adhesive	Standard to Heavy Duty Adhesive
Standard Adhesive	50kg.	50 kg.	50 kg.	20 Kg
Portland Cement	75 kg.	75 kg.	75 kg	0
Fine Filler, 20-100#	0.5-1	2	4	0
Multicrete CM, Kg	As per need	As per need	As per need	0.2-4
Water	62 ltr.	62 ltr.	65 ltr.	As per need
Typical Yield	Multichem	Multichem	C2F	10 ltr.
Standard				Normal to C2F

6. TILE GROUT

Recommended mixes:

Description	Standard Tile Grout	Flexible Tile Grout	Ready Made Tile Grout
Tile Grout	50kg.	50 kg.	1 Kg Pack
Portland Cement	70 kg.	70 kg.	0
Fine Filler, 20-100#	0.5	4	0
Multicrete CM, Kg	As per need	As per need	50 gm- 200 gm
Water	60 ltr.	60 ltr.	As per need
Typical Yield	Multichem	Multichem	1/2 ltr.
Standard			Multichem



MULTICHEM GROUP | 1, 1st Floor, Kirtida Bungalow, Nahur Stn Road, Beside SBI Bank, Bhandup (E), Mumbai-400042, Phone No.: 91-22-25669137, 25664890, e-mail: info@multichemgroup.net, www.multicretecm.com, www.multichemgroup.net

Multicrete CM/1997/R2-13/5/2018

7. Crack Repair Product

Recommended mixes:

Description	Standard Product	Flexible Product
Portland Cement Fine Filler, 20-100# Multicrete CM Water Typical Yield Standard	1 kg. 2 kg. 100 gm As per need 1.5 ltr. Multichem	1 kg. 1 kg. 200 gm As per need 1 ltr. Multichem

8. Bonding Agent

Recommended mixes:

Description	Standard Product	Flexible Product
Portland Cement Fine Filler, 20-100# Multicrete CM Water Typical Yield Standard	1 Kg 1 Kg 1 Kg As per need 1.5 ltr. Multichem	1 Kg 1 Kg 1 Kg As per need 1 ltr. Multichem

9. Engineering Grout

Recommended mixes:

Description	Standard Product	Flexible Product
Portland Cement Washed Sand Aggregates Multicrete CM Water Typical Yield Standard	50 Kg 75 Kg 75-150 Kg As per need 1.5 ltr. Multichem	50 Kg 1 Kg 1 Kg As per need 1 ltr. Multichem

10. SEALANT

Recommended mixes:

Description	Standard Product	Flexible Product
Filler, 100-200# Multicrete CM Typical Yield Standard	80 Kg 50 Kg ** Multichem	60 Kg 50 Kg ** Multichem

APPLICATION DATA:

1. Surface Preparation: Mechanically remove all damaged concrete back to a sound core. Whenever possible, the full circumference of the steel reinforcement should be exposed to at least 25mm behind the bars and 50mm beyond the point at which corrosion is visible. On cutting back, feather edges must be avoided. The perimeter of repair area should be stepped to a depth of 10 mm by means of saw or disc cutting or preferably using a power chisel. The areas to be repaired must be free from all unsound materials i.e. dust, oil, grease, corrosions by-products and organic growth. Smooth cut surfaces should be roughened, all loose materials and surface laitence removed and reinforcement cleaned to bright steel. Shot blasting or grit water jetting is recommended, but for some smaller areas needs gunning or bush hammering is effective. The strength of the concrete sub-base should be a minimum of 20 N/mm sq.

The prepared substrate should be thoroughly soaked with clean water until uniformly saturated without any standing water.

2. Priming/Bonding: Where necessary, two coats of MULTIBOND S (steel reinforcement protector) should be applied to the prepared steel, by brush, as described in the individual data sheet. Where the substrate exhibits high porosity or is absorbent, the pre dampened surface should be primed with a thin slurry consisting of one part of **MULTICRETE® CM**, 1 part water and 2 part ordinary Portland cement mixed to give a thin emulsion consistency

(Coverage 10-15sqmt/Kg of **MULTICRETE® CM**)

Allow to become dull before continuing with application and remove any excess material lying in rough, broken or irregular surfaces. The subsequent rendering, screeds, etc. should be applied on wet basis.

3. Mixing: Mortar and screed, made with **MULTICRETE® CM**, should be mechanically mixed, using a forced action pan mixer in a clean drum, using a drill and paddle. A normal concrete mixture is not suitable. Shake Multicrete CM before use and then pour



MULTICRETE[®] CM

Single Component Cement Mixes Modifier
Product Code No.:M-0303

the required quantity into the mixing container and add equal volume of water. Slowly add the required amount of sand and cement, and if necessary, coarse aggregates as determined from the mix design guide and mix until homogeneous. Continue to mix and add the minimum of extra water required to give the desired workability, to enable correct working and compaction. A water / cement ratio of less than 0.4 is advised. Normal mixing time depends upon the type of mixer used 2-3 minutes is an average. Mix so as to entrain as little air as possible. Use without delay.

4. Application: Mortar or screed should be applied so as to remove entrapped air, in layer, not exceeding 50mm thickening.

If necessary, support with shuttering to allow for compaction. For repairs, which require multi- layers application, it is important to ensure that previous layers are well keyed and hardened but not fully cured prior to the application of subsequent layers. Final profiling should be carried out with wooden float or steel trowel.

5. Curing: Normal concreting procedures should be strictly adhered to. It is important that the surface of the mortar or screed coating is protected from strong sunlight and drying winds with polythene sheets, damp hessian or similar. Alternatively, for flooring applications, a 300-600 micron silica sand can be cast liberally onto the surface (approximately 2kg/sqmt) taking care to ensure that the sand does not penetrate the full depth of the coating. This provides effective curing, whilst also providing a hard wearing, non-slip finish. Allow a minimum of 72 hours curing of the material and ensure the moisture content of the surface is less than 20%.

6. Limitations: Do not apply below 5°C or when temperatures of substrate, air or topping may fall below 5°C within 8 hours of application. Do not apply against hydrostatic pressure from behind the slab if leakage is expected, material may get washed away. Do not apply **MULTICRETE[®] CM** when rain expected within 3 hours of application, or if material is yet to get cured.

7. Handling, Clean-up: Clean tools immediately after use with clean water. Avoid skin and eye contact. Use with adequate ventilation. Observe all safety handling, storage and personal protection guidelines as detailed in the Material Safety Data Sheets provided with this product. Temperature affects curing, handling and spreading.

STORAGE:

Store in dry, frost-free conditions at moderate temperature not **greater** than 25 °C.

SAFETY DATA:

- Irritating to eyes, respiratory systems and skin.
- Risk of serious damage to eyes.



MULTICHEM GROUP | 1, 1st Floor, Kirtida Bungalow, Nahur Stn Road, Beside SBI Bank,
Bhandup (E), Mumbai-400042, Phone No.: 91-22-25669137, 25664890,
e-mail: info@multichemgroup.net, www.multicretecm.com, www.multichemgroup.net

Multicrete CM/1997/R2-13/5/2018



MULTICRETE® CM

Single Component Cement Mixes Modifier
Product Code No.:M-0303

- Keep out of reach of children. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice.
- After contact with skin, wash immediately with plenty of clean water.
- Wear suitable protective clothing, gloves and eye/face protection.

Please consult our technical department for further information.

WARRANTY

Multichem warrants **MULTICRETE® CM** to be free from manufacturing defects as defined in this warranty. Manufacturing defects are considered to be those defects that occur due to the quality of the ingredients or from the manufacturing process itself. This warranty does not include labor costs and other costs or expenses associated with the removal or installation of **MULTICRETE® CM**.

Because the Multichem does not perform the actual installation, it cannot be held responsible for the results of the application. Multichem specifically disclaims problems that occur due to weather conditions, structural movement, structural design flaws and application techniques.

This warranty is in lieu of all other warranties expressed or implied including the warranty of merchantability and fitness of purpose and of all other obligations or liabilities on Multichem part. Multichem neither assumes nor authorizes any person to assume for Multichem any liability in connection with the sale and installation of **MULTICRETE® CM**.

Because of constant improvement of manufacturing techniques and formulations, Company reserves rights to change this datasheet and its contents without prior notice.



MULTICHEM GROUP | 1, 1st Floor, Kirtida Bungalow, Nahur Stn Road, Beside SBI Bank,
Bhandup (E), Mumbai-400042, Phone No.: 91-22-25669137, 25664890,
e-mail: info@multichemgroup.net, www.multicretecm.com, www.multichemgroup.net

Multicrete CM/1997/R2-13/5/2018